

2810 Clark Avenue • St. Louis, MO 63103-2574 • (314) 531-8080 • FAX (314) 531-8085
 Chemical, Metallurgical, Mechanical, Nondestructive, Environmental Testing, Analyses and Field Service.

ARCOPLAST
 1873 Williamstown Drive
 St. Peters, MO 63376

May 21, 2020
 Lab No. 20P-2156
 Invoice No. 270963
 Page 25 of 26

Attention: Ghislain Beauregard

REPORT OF MECHANICAL TEST

Groups 20, 21, 22: 3 ea. Arcoplast GFRMC Panel
Groups 34, 35: 2 ea. Arcoplast Acryloyl EP Panel
SUBJECT: Impact Resistance (2lb Steel Ball Dropped Causing No Damage)
METHOD: Mil 1073.2
RESULTS:

Sample	Sample Size	Maximum Height (ft)
Group 20	3"x 6"x5mm	1
Group 21	6"x 8"x6mm	1
Group 22	6"x 8"x9.5mm	1.5
Group 34	6"x 6.5"x 9.5mm Laminated to 9.5mm	13
Group 35	6"x 6.5"x 12.5mm Laminated to 12.5mm	28


 Karl Schmitz, Director
 Materials Testing

KS/jlb