

2810 Clark Avenue • St. Louis, MO 63103-2574 • (314) 531-8080 • FAX (314) 531-8085
 Chemical, Metallurgical, Mechanical, Nondestructive, Environmental Testing, Analyses and Field Service.

ARCOPLAST
 1873 Williamstown Drive
 St. Peters, MO 63376

May 21, 2020
 Lab No. 20P-2156
 Invoice No. 270963
 Page 17 of 26

Attention: Ghislain Beauregard


REPORT OF MECHANICAL TEST

Group 9:

Arcoplast GFRMC Panel 5mm

SUBJECT: Tensile Strength Test
METHOD: ASTM D638-14
INSTRUMENT: Instron 5500R with Bluehill software
RESULTS:

Specimen #	Area (in ²)	Max Load (lbf)	Tensile Strength (psi)	Modulus (psi)
1	0.095	960	10100	127866.8
2	0.096	1254	13100	204299.7
3	0.090	1139	12600	181703.4
4	0.098	1378	14100	232755.0
5	0.093	1001	10800	103374.8
Average		960	10100	103374.8




 Karl Schmitz, Director
 Materials Testing

KS/jlb