

ARCOPLAST
1873 Williamstown Drive
St. Peters, MO 63376

June 10, 2020
Lab No. 20E-0980
Invoice No.
Page 4 of 10

Attention: Ghislain Beauregard

REPORT OF ANALYSIS

Group 32:

Arcoplast GFRMC 9.5 mm High Gloss Finish

SUBJECT: Water Absorption, 24-Hour Immersion

TEST METHOD: ASTM D 570-98

CONDITIONING: 24 hours at 50 °C / Alcohol Wipe

SAMPLE	Immersion Time (hrs)	Total Water Absorption (% by wt.)
TEST I	24	27.7
TEST II	24	46.5
TEST III	24	18.4
AVERAGE	----	30.9